



TECHNICAL DATA

ArmaPET[®] Eco

ArmaPET Eco combines insulation and structural integrity, ensuring energy and emission efficiency for decades of use.

- // Secured lifetime insulation performance
- // Prevents degradation by moisture, rodents and insects
- // Robust material allows fast and easy handling
- // 100% recycled material supports industry environmental and sustainability directives
- // Full range availability anywhere and at any time

www.armacell-core-foams.com



 **armacell**[®]
ArmaPET[®]

ARMAPET ECO

Energy-efficient composite sandwich structures are a powerful way of **saving energy and reducing CO₂ emissions**. Armacell is following the growing demand for high-performance insulating materials and with ArmaPET Eco it offers a foam core that optimally combines structural performance, versatility, sustainability, and long-term insulating properties.

The potential list of applications using ArmaPET Eco is practically endless, from super-structures of refrigerated and recreational vehicles, to industrial halls, radomes, bath pods, food trolleys and many more.

ArmaPET Eco cored sandwich panels improve the performance, functionality and sustainability of the final application in many ways:

- // Long-term stability of insulation properties and low thermal conductivity secure lifetime insulation performance
- // Closed cell structure minimises moisture penetration and degradation by rodents and insects
- // Compatibility with most production methods and resin systems allows for individual manufacturing processes and material combinations
- // Solvent stability provides resistance to most acids, salts and fuels
- // The homogenous surface solves possible print-through challenges when using thin and glossy outer skins
- // Low weight makes it possible to build lighter vehicles and maximise the payload
- // Excellent screw retention allows for conventional fixing methods

FOR CONSTANT TEMPERATURE

Wherever efficiency and safety in the refrigeration supply chain are required, or resource-saving construction is called for, Armacell offers a full range of eco-efficient product solutions, providing benefits in energy consumption and emissions during temperature-controlled operation.

ArmaPET Eco in the superstructure of caravans and mobile homes keeps the loss of heat and cold to a minimum, ensuring a comfortable stay. Additionally, ArmaPET lowers the structural weight, thus enhancing fuel consumption, reducing CO₂ emissions or increasing payloads, all key drivers for reduced overall life-cycle costs.

FOR SUSTAINABLE BUILDING

ArmaPET Eco is the suitable core material for all kinds of prefabricated structural insulated panels in the building envelope, floors and internal partitions. In addition to its long-term insulation and structural integrity, additional key benefits are its thermoformability into curved shape and its versatility with almost any type of finishing options.

ArmaPET Eco helps create buildings that are more energy efficient, durable, faster to build, and have a lower lifecycle cost and reduced environmental impact.

Technical Data

ArmaPET Eco

			Eco65	Eco75	Eco95	Eco110	Eco130	Eco145	Eco195
Density	ISO 845	kg/m ³	65 ⁽¹⁾	75 ⁽²⁾	95 ⁽²⁾	110 ⁽²⁾	130 ⁽²⁾	145 ⁽³⁾	195 ⁽³⁾
		lb/ft ³	4.1 ⁽¹⁾	4.7 ⁽²⁾	5.9 ⁽²⁾	6.9 ⁽²⁾	8.1 ⁽²⁾	9.1 ⁽³⁾	12.2 ⁽³⁾
Compression Strength Z	ISO 844	MPa	0.2	0.3	0.45	0.6	0.8	1.05	1.8
		psi	30	45	65	85	115	150	260
Compression Modulus Z	ISO 844	MPa	9	13	15	21	32	43	66
		psi	1'305	1'885	2'175	3'045	4'640	6'235	9'570
Shear Strength YZ	ISO 1922	MPa	0.3	0.4	0.5	0.55	0.7	0.85	1.15
		psi	45	60	75	80	100	125	165
Shear Modulus YZ	ISO 1922	MPa	5	9	11	14	18	24	34
		psi	725	1'305	1'595	2'030	2'610	3'480	4'930
Shear Elongation YZ	ISO 1922	%	15	14	12	10	8	7	5
		%	15	14	12	10	8	7	5
Shear Strength XZ	ISO 1922	MPa	0.3	0.45	0.6	0.75	0.9	1.1	1.25
		psi	45	65	85	110	130	160	180
Shear Modulus XZ	ISO 1922	MPa	8	13	18	23	30	34	41
		psi	1'160	1'885	2'610	3'335	4'350	4'930	5'945
Shear Elongation XZ	ISO 1922	%	10	8	8	8	7	7	4
		%	10	8	8	8	7	7	4
Tensile Strength Z	ASTM C 297	MPa	0.55	0.7	1.05	1.2	1.35	1.5	1.9
		psi	80	100	150	175	195	220	275
Tensile Modulus Z	ASTM C 297	MPa	11	14	22	32	40	47	70
		psi	1'595	2'030	3'190	4'640	5'800	6'815	10'150
Thermal Conductivity	at 23 °C	W/(m·K)	0.031 ⁽⁴⁾	0.031 ⁽⁴⁾	0.032 ⁽⁴⁾	0.032 ⁽⁴⁾	0.034 ⁽⁴⁾	0.035 ⁽⁴⁾	0.038 ⁽⁴⁾
		at 73.4 °F	BTU.in/FT ² .hr.°F	0.215 ⁽⁴⁾	0.215 ⁽⁴⁾	0.222 ⁽⁴⁾	0.222 ⁽⁴⁾	0.236 ⁽⁴⁾	0.243 ⁽⁴⁾
Reaction to fire	EN 13501-1	Class	E ⁽⁵⁾	E ⁽⁵⁾	E ⁽⁵⁾	E ⁽⁵⁾	E ⁽⁵⁾	E ⁽⁵⁾	E ⁽⁵⁾

Board dimensions

Standard = 1015 x 2448 mm / 39.96 x 96.38 inch.

Customer specific dimensions available on request.
Standard thicknesses are from 55 to 66 mm, other thicknesses are available on demand (special request).

Tolerances at room temperature

Width = +/- 10 mm +/- 0.39 inch

Length = -7/+20 mm -0.28/+0.79 inch

(1) Tolerances: +/- 10 kg/m³, +/- 0.6 lb/ft³

(2) Tolerances: +/- 5 kg/m³, +/- 0.3 lb/ft³


(3) Tolerances: +/- 5%

(4) Based on a single test result. To be used for information only.

(5) Tested according to EN ISO 11925-2 at a thickness of 25 mm / 0.98 inch.

Further information available on request.

All values are average production figures. Based on extrusion thickness 55-66 mm, with changing extrusion thickness mechanical properties can vary.
Our products are CFC / HFC free.
Physical properties are not affected by variances in colour.
Customs tariff code: 39.21.19.00



All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2021. All rights reserved. ® is a trademark of the Armacell Group and is registered in the U.S. and other countries.
00492 | ArmaPET Eco | ArmaPET | C_TDS | 122021 | Global | EN Master

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,000 employees and 23 production plants in 15 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more company information, please visit:
www.armacell.com

For product information, please visit:
www.armacell-core-foams.com

