

AUTOMOTIVE



Monarch® #8002

- ASTM D 1056-07 2A2 grade closed cell material
- Fine cell – manufactured in blocks (buns)
- Medium density, pure EPDM material
- Excellent resistance to ozone, UV, weathering and elevated temperatures
- Approved source for Delphi SD2-207, paragraph 6.7
- ASTM D 6576-07 Type II, Grades B & C, condition soft-medium

Monarch®

General Information

Armacell Monarch® #8002: Armacell LLC (Spencer, WV Plant) manufactures a black, closed cell, $9 \pm 2 \text{ lb./ft}^3$ ($144 \pm 32 \text{ kg/m}^3$) density pure EPDM rubber product #8002, that meets all the requirements of ASTM D 1056-07 2A2 and SAE J18 APR2002 2A2. #8002 has excellent resistance to ozone. #8002 is manufactured with non-staining oils and anti-oxidants. #8002 does not incorporate a flame retardant but meets the requirements of FMVSS-302 at 0.125" (1/8") (3.1 mm) and higher.

Bun Size Information

Product	Bun Size (Inches)			Bun Size (mm)			Color
	W	L	T	W	L	T	
8002	40	54	2	1016	1372	50.8	Black

Automotive and Industrial Specifications

The following is a list of automotive and industrial specifications that Armacell Monarch® #8002 has been tested to or can meet. Additional specifications are listed that have a few exceptions. Feel free to suggest other automotive, military or industrial specifications, and a full review will be made.

Source	Specification	Armacell Monarch® #8002	Comments
ASTM	ASTM D1056-07	2A2	Additional (optional) suffixes can be added
ASTM	ASTM G21-09	Pass, rating 0	Fungus resistance test method
ASTM	ASTM D 925	Pass, no migration staining	Method B
ASTM	ASTM D 1149	Pass, no cracking, rating 0	Ozone resistance test method
ASTM	ASTM D 1171	Pass, no cracking, rating 0	Ozone resistance test method
ASTM	ASTM D 6576-07	Type II, Grades B & C, condition soft-medium	Formerly MILR6130-C
Chrysler	Chrysler MSZ-75 J18	2A2	Additional (optional) suffixes can be added
Chrysler	Chrysler MS JP9-4	Meets at thicknesses of 0.125" (1/8") (3.1mm) & higher	Flame resistance (horizontal burn rate)
Chrysler	Chrysler MSAY 430	Type 4	On approved source list
Delphi	SD2-207	Paragraph 6.7	See note 4. On approved source list
Federal	FMVSS-302	Meets at thicknesses of 0.125" (1/8") (3.1mm) & higher	Flame resistance (horizontal burn rate). See note 3
FORD	FORD WSK M2D 419-A	Type 3	See note 2
GM	GME 60-251	2A2U, pass, grade 0	Ozone Test
GM	GM 6086-M	Type II	CD tested at 50% deflection. See note 1
GM	GM 6090-M	(B4A) Meets at thicknesses of 0.125" (1/8") (3.1mm) and higher	Flame resistance tested per GM 9070-P (horizontal burn rate)
GM	GMN11106	Type II	CD tested at 50% deflection. See note 1
GM	GMW15473	Class I Type IV	CD tested at 50% deflection. See note 1
Hyundai	Hyundai MS260-13	Classification ER	Additional (optional) suffixes can be added
ISO	ISO 6916	2A2	No exceptions
Military	ASTM D 6576-07	Type II, Grades B & C, condition soft-medium	Formerly MILR6130-C
SAE	SAE J18 APR2002	2A2	Additional (optional) suffixes can be added
SAE	SAE J369	Meets at thicknesses of 0.125" (1/8") (3.1mm) & higher	Flame resistance (horizontal burn rate)
SAE	SAE J 1351	Rating 2	Odor specification
Toyota	TSM 1501G	2A2	No exceptions
Toyota	TSM 0500G	Meets at thicknesses of 0.125" (1/8") (3.1mm) & higher	Flame resistance (horizontal burn rate)

Note 1: For all GM 6086-M, GMN11106 & GMW15473 callouts, Armacell Monarch® certifies to the "basic" requirements only. Request additional information for each product. Providing application (interior, exterior or under-hood) and part thickness is helpful.

Note 2: For all FORD WSK M2D 419-A callouts, request full information for each product due to some exceptions with non-tested staining requirements.

Note 3: A number of horizontal burn tests can also be listed (GM 6090, BMW, Volvo, etc.). Request additional information.

Note 4: See QMPL-3621 Revision 12. Effective date August 24, 2009.



Polymer Base: **Pure EPDM**

F-08002 (Black)

Physical Properties	Unit	Test Method	Typical Results
Density	kg/m ³	ASTM D 1056	144 ± 32
	lb/ft ³	ASTM D 1056	9 ± 2
Hardness, Durometer Shore 00		ASTM D 2240	53 ± 5
Compression Deflection (25%)	kPa	ASTM D 1056	48 ± 14
	psi	ASTM D 1056	7 ± 2
Compression Set (Room temp)	%	ASTM D 1056	≤ 25%
Tensile Strength	kPa	ASTM D 412 (Die A)	520
	psi	ASTM D 412 (Die A)	75
Tear Strength	kN/m	ASTM D 624 (Die C)	2.1
	lb/in	ASTM D 624 (Die C)	12
Elongation	%	ASTM D 412 (Die A)	150%
Resilience	%	ASTM D 2632	45%
Service Temperature			
Low	°F (°C)	ASTM D 746	-70°F (-56.7°C)
High Continuous	°F (°C)	ASTM D 746	220 °F (104.4°C)
High Intermittent	°F (°C)	ASTM D 746	250°F (121.1°C)
Water Absorption			
Maximum Weight Change	%	ASTM D 1056	< 10%
Fluid Immersion (7 days at 23°C [73.4°F])			
ASTM Ref. Fuel B, Weight Change (%)	%	ASTM D 1056	Not Applicable
Accelerated Aging (7 days at 70°C [158°F])			
Flexibility (180° bend without cracking)		ASTM D 1056	Pass
Appearance change		ASTM D 1056	None
Change in Compression Deflection	%	ASTM D 1056	± 30%
Combustion Characteristics		Thicknesses	Comments
FMVSS-302		0.125" (3.1 mm) & higher	Pass

ASTM D 1056 designation: 2A2
 SAE J 18 APR2002 designation: 2A2
 ASTM D 6576: Type II, Grades B & C, Condition Soft-medium
 EPDM = (ethylene-propylene-diene-methylene)

ARMACELL LLC
 TEL: 1 800 866-5638
 FAX: 919 304-3847
 info.us@armacell.com
 www.armacell.us
 7600 Oakwood Street Extension • Mebane, NC 27302



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice.