



INSULATION JUST GOT BETTER

ArmaGel HT

Flexible aerogel blanket for high-temperature applications

- // ASTM C1728 compliant
- // Hot conditions up to 650 °C (1200 °F)
- // More choice: 5, 10, 15 and 20mm thicknesses
- // Up to five times better thermal performance than competing insulation materials
- // Mitigates the risk of corrosion under insulation (CUI)

www.armacell.com/armagel



 **armacell**[®]
ArmaGel

INSULATION JUST GOT BETTER


ArmaGel HT

Welcome to the next generation of aerogel blanket technology. Flexible and bendable. Environmentally safe. Designed for incombustibility. Superior thermal performance. Hot conditions up to 650 °C (1200 °F) is no sweat. ArmaGel HT is the reliable solution for high-temperature applications.

High-temperature



Flexible



Hydrophobic



[Learn more.](#)

AEROGEL

Used by NASA to bring home a piece of a comet because it's strong enough to stop a bullet in its track, aerogel offers an uncanny array of physical properties - thermal, acoustical - and so holds incredible potential for insulation uses. As the name suggests, aerogel is a solid derived from gel in which the liquid component of the gel has been replaced with air making it dry and porous. In fact, over 90 percent of the volume is empty space making aerogel the world's lightest solid material. It's also 1,000 times less dense than glass, making it the world's lowest density solid material.

UP TO
80%

THINNER
than competing
insulation products

UP TO

5x

SUPERIOR THERMAL
PERFORMANCE
than competing
insulation products

4

THICKNESSES
FOR THE
BEST FIT



YOUR BENEFITS

// Increase coverage

New sizes and more choice. 10mm thickness available today. 5, 15 and 20mm coming soon. A thicker layer gives more insulation coverage per man hour than traditional aerogel insulation.

// Reduce labour cost

Cuts easily and conforms to preferred shapes, with less wastage, making it the right fit for installers.

// Reduce downtime

Product removal is made simple, reducing both downtime and the need to purchase replacement insulation during regular maintenance cycles.

// Superior thermal performance

Offering up to 5 times superior thermal performance versus like-for-like competing insulation products.

// Hydrophobic and breathable

Repels liquid water, but allows vapour to escape, helping to keep equipment drier for longer.

// Ultra-thin and ultra-light

Equal thermal performance at a fraction of the thickness. Improved handling and easier transportation.

// Versatile

More flexibility than traditional aerogel insulation materials.

// Environmentally safe

Chloride-free and landfill disposable.

// CUI defence

Hydrophobicity and breathability enhance protection against corrosion under insulation (CUI).

TECHNICAL DATA - ARMAGEL HT

Brief description	ArmaGel HT is a flexible aerogel blanket suitable for elevated temperature applications with maximum operating temperatures up to 650°C (1200°F). ArmaGel HT is compliant to ASTM C1728, Type III, Grade 1A.
Material type	Aerogel blanket.
Product colour range	Grey
Special features	ArmaGel HT is resistant to elevated operating temperatures up to 650 °C (1200 °F). The product is suitable for use in multi-layer applications including ArmaSound Industrial Systems.
Product range	Sheets in rolls, 5, 10, 15 and 20 mm (0.2, 0.4, 0.6, 0.8 in) thickness and width of 1.5 m (59 in). For further details, please refer to the product range tables at the end of this document.
Applications	Thermal insulation/protection of pipes, vessels and ducts (including elbows, fittings, flanges etc.) in offshore, onshore, industrial (typically oil and gas) and process equipment facilities. ArmaGel HT is also used as a component of ArmaSound Industrial Systems to provide acoustic insulation on industrial pipework and vessels, ensuring reduction of sound transmission.
Installation	For industrial applications it is recommended to consult the relevant Armacell application manual(s). For further information please contact our Technical Services.

Property	Value / Assessment										Standard / Test method
Temperature range											
Service temperature ^{1,2,3,4}	Max. °C					Max. °F					ASTM C411, ASTM C447
	650					1,200					
Thermal conductivity											
Declared thermal conductivity ⁵	Thickness	24°C (75°F)	38°C (100°F)	93°C (200°F)	149 °C (300°F)	204°C (400°F)	260°C (500°F)	316°C (600°F)	371°C (700°F)	ASTM C177	
	$\lambda d \leq$ [W/ (m·K)]	0.021	0.022	0.023	0.025	0.029	0.032	0.036	0.043		
	$k \leq$ [Btu-in/ (h-ft ² -°F)]	0.14	0.15	0.16	0.18	0.20	0.22	0.25	0.30		
Temperature resistance											
Hot surface performance ²	Pass										ASTM C411
Linear shrinkage under soaking heat	<2% in width and length										ASTM C356
Fire Performance and Approvals											
Reaction to fire	B-s1,d0										EN 13501-1 ²
Surface burning characteristics	\leq 5 flame spread index \leq 10 smoke development										ASTM E84
Resistance to water vapour											
Water vapour sorption	\leq 5% by weight										ASTM C1104
Resistance to water											
Hydrophobic	Yes										
Water absorption	Pass										ASTM C1763
Corrosion mitigation											
Corrosiveness to steel	Passed, Mass Loss Corrosion Rate (MLCR) not exceeding that of 5 ppm chloride solution on carbon steel coupon										ASTM C1617, Procedure A
Stress corrosion cracking	Pass										ASTM C692, ASTM C795
Physical attributes											
Nominal density	180 kg/m ³ (11 lb/ft ³)										ASTM C303

Property	Value / Assessment	Standard / Test method
Mechanical properties		
Compressive strength ⁴	≥ 3 psi/ 20.7 kPa at 10% compression	ASTM C165
Flexibility of insulation blankets	Flexible	ASTM C1101
Weather and UV resistance		
Weather resistance	In all industrial applications the outer layer of the material must be protected with an adequate covering like metal jacketing or preformed UV-cured GRP (Glass-Reinforced Plastic) cladding. Please contact Technical Services for guidance on the temperature limitations and specific construction considerations which need to be made for each jacketing system.	
Health and environment		
Fungal growth	No growth	ASTM C1338
Health aspects	Neutral	
Other technical features		
Shelf life ⁷	Max. 3 years	
Storage	Material shall be stored indoors, in clean and dry conditions, away from direct sunlight.	

¹For use in temperatures beyond the published value, please contact Technical Services.

²For operating temperatures above 400 °C (752 °F) a metallic foil barrier with 0.05 mm (0.002 inch) thickness must be additionally installed. For details please contact Technical Services.

³For live line installations, refer to the ArmaGel HT and HTL application manual.

⁴ArmaGel HT is designed for application where the operating temperatures are above ambient. In the event that the operating temperatures are below ambient please consult our technical services for further information and support.

⁵Measured under a load of 1.5 kPa (0.22 psi).

⁶Test performed with a preload of 13.8 kPa (2 psi).

⁷Shelf life (maximum storage time) is limited to ensure that only currently manufactured products are installed on projects. This limitation is restricted solely to storage of the product and does not affect the lifetime of product after it has been installed.

Roll - jumbo

Item	Thickness [mm]	Thickness [Inch]	Width (m)	Width [inch]	Length [m]	Length [ft]	Content [metric]	Content [imperial]
AGH-05-00/150P	5	0.2	1.5	59	65	213.3	97.5 m ²	1049.5 ft ²
AGH-10-00/150P	10	0.4	1.5	59	40	131.2	60 m ²	645.8 ft ²
AGH-15-00/150P	15	0.6	1.5	59	26	85.3	39 m ²	419.8 ft ²
AGH-20-00/150P	20	0.8	1.5	59	20	65.6	30 m ²	322.9 ft ²

Other information

Thickness tolerance 5 mm (0.2 in) nominal thickness: ± 1 mm
10 mm (0.4 in) nominal thickness: ± 2.5 mm
15 mm (0.6 in) nominal thickness: ± 3 mm
20 mm (0.8 in) nominal thickness: ± 4 mm

Length tolerance ± 5%

Width tolerance ± 3%

Roll - standard

Item	Thickness [mm]	Thickness [Inch]	Width (m)	Width [inch]	Length [m]	Length [ft]	Content [metric]	Content [imperial]
AGH-05-00/150S	5	0.2	1.5	59	16	52.5	24 m ²	258.3 ft ²
AGH-10-00/150S	10	0.4	1.5	59	8	26.2	12 m ²	129.2 ft ²
AGH-15-00/150S	15	0.6	1.5	59	6	19.7	9 m ²	96.9 ft ²
AGH-20-00/150S	20	0.8	1.5	59	4	13.1	6 m ²	64.6 ft ²

Other information

Thickness tolerance 5 mm (0.2 in) nominal thickness: ± 1 mm
10 mm (0.4 in) nominal thickness: ± 2.5 mm
15 mm (0.6 in) nominal thickness: ± 3 mm
20 mm (0.8 in) nominal thickness: ± 4 mm

Length tolerance ± 5%

Width tolerance ± 3%

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our Data Protection Policy.

Trademarks followed by © or ™ are trademarks of the Armacell Group. © Armacell, 2023 All rights reserved.

ArmaGel | ArmaGel HT | Brochure | 122023 | en-IN

ABOUT ARMACELL

As the inventor of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With more than 3,300 employees and 27 production plants in 19 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for acoustic and lightweight applications, recycled PET products, next-generation aerogel technology and passive fire protection systems.

For more information, please visit:
www.armacell.com

